



Saremco print CROWNTEC

Technical Data

| | |
|-------------------------------------|---|
| Consistency | middle viscos homogeneous liquid |
| Colour | According to Vita Shades (A1, A2, A3, A3.5, B1, Snow White (Bleach)) |
| Depth of cure (DIN EN ISO 4049) | ≥ 1,5 mm |
| Flexural strength (DIN EN ISO 4049) | > 130 MPa |
| E-Modulus (DIN EN ISO 4049) | > 4000 MPa |
| Barcol-Hardness | > 40 |
| Shelf-life | 3 years |